



## TECHNICAL INFORMATION

|                                    |  |
|------------------------------------|--|
| <b>BRICK NAME</b>                  | <b>CATEGORY 8 COMPRISING OF:</b><br>2½" Georgian<br>2½" Reclamation Georgian*<br>2⅝" Reclamation Cheshire*   |
| <b>BRICK TYPE</b>                  | Through colour clay handmade brick   |
| <b>SPECIFICATION</b>               | Manufactured to BS EN 771-1:2011   |
| <b>SIZE*</b>                       | 228 x 114 x 65mm   |
| <b>DIMENSIONAL TOLERANCE:</b>      | T1   |
| <b>RANGE:</b>                      | R1   |
| <b>COMPRESSIVE STRENGTH</b>        | Mean - 30 N/MM <sup>2</sup>  |
| <b>WATER ABSORPTION</b>            | Mean - 11%   |
| <b>SOLUBLE SALT CLASSIFICATION</b> | S2   |
| <b>PACKAGING</b>                   | Shrink wrapped on wooden pallets in packs of 576/±500  |
| <b>PACK SIZE; LxWxH</b>            | 1100 x 1100 x 1100mm Approx.   |
| <b>PACK WEIGHT</b>                 | 1.85 / ±1.7 Tonnes Approx.   |
| <b>USAGE</b>                       | Always mix from several packs, working vertically down the blades, not horizontally across the tops of the packs   |
| <b>SAMPLES</b>                     | Samples will be supplied on request  |
| <b>DURABILITY</b>                  | F2   |
| <b>PERFORMANCE</b>                 | The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed.<br>Liability cannot be accepted for the performance of the product if used outside our recommendations.<br>Guidance on the use of these bricks in specific situations is readily available from us. |

\*Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in the relevant European Standard.

11.2018

